



High performance Materials



## Physical Properties & Compound Comparison

Compounds	Gumlast® L8010	Kalrez® 6375	Chemraz® 505	Chemraz® 605
Maximum Service Temperature, °C (°F)	275°C (527°F)	275°C (527°F)	230°C (446°F)	260°C (500°F)
Durometer Hardness, Shore A, points ± 5	75	75	80	80
100% Modulus, MPa	11.0	7.2	7.9	9.0
Tensile Strength @Break, MPa	18.0	15.2	12.1	14.8
Elongation @ Break, %	180	160	140	130
Compression Set % 70 hr @ 204°C (400°F)	17	30	25	20

Gumlast® is registered trademark of FloDynamix LLC.

Kalrez® is registered trademark of DuPont Performance Elastomers

Chemraz® is registered trademark of Greene-Tweed Corporation

The information provided here is to best of our knowledge accurate and reliable. FloDynamix LLC makes no warranty, expressed or implied that parts made from this material will perform in customer's application. It is the customer's responsibility to evaluate parts prior to use. Gumlast® is registered trademark of FloDynamix LLC. Please visit us at [www.flodynamix.com](http://www.flodynamix.com)