

# GUMLAST®

***Perfluoroelastomer sealing solution at fraction of the cost!***

## ***Physical Properties & Compound Comparison***

Compounds	Gumlast® L8015	Chemraz® 513	Kalrez® 8085	Kalrez® 2037
Maximum Service Temperature, °C (°F)	260°C (500°F)	210°C (410°F)	240°C (464°F)	220°C (428°F)
Durometer Hardness, Shore A, points ± 5	80	80	80	79
100% Modulus, MPa	3.6	7.2	7.5	6.2
Tensile Strength @Break, MPa	7.1	11.0	16.3	16.9
Elongation @ Break, %	185	165	159	200
Compression Set % 70 hr @ 204°C (400°F)	13	25	42	27

Gumlast® is registered trademark of FloDynamix LLC a division of Nugentec LLC

Kalrez® is registered trademark of DuPont Performance Elastomers

Chemraz® is registered trademark of Greene-Tweed Corporation

The information provided here is to best of our knowledge accurate and reliable. Nugentec makes no warranty, expressed or implied that parts made from this material will perform in customer's application. It is the customer's responsibility to evaluate parts prior to use.

Gumlast® is registered trademark of FloDynamix LLC, a division of Nugentec LLC. Please visit [www.nugentec.com](http://www.nugentec.com) , [www.flodynamix.com](http://www.flodynamix.com)